

VISCOM-DIGITAL - Wide Format Ink Jet Print Media

Issue date : 05/01/2005
Date last modification : 23/01/2012

04061 RI-JET 50 CAST WHITE ASP26 PERMANENT GREY WKPE144
Face Material

Gloss white CAST soft vinyl.

| | |
|-------------------|----------------------------------|
| Type | Soft vinyl |
| Colour and Finish | Gloss white CAST |
| Weight | 70 g/m ² ±10% ISO-536 |
| Thickness | 50 µ ±10% ISO 534-80 |

Adhesive

Solvent based acrylic permanent adhesive with grey pigments featuring high cohesion and good water resistance. Designed for a wide variety of substrates such as glass, ABS, PS, PVC. Unsuitable for apolar surfaces (like PE and PP).

| | |
|------------------|----------------------------|
| Reference | ASP26 permanent GREY |
| Type | Acrylic permanent |
| Min. Appl. Temp. | +10°C |
| Service Temp. | -20°C/+130°C |
| Shear | High |
| Tack | Medium N/inch ² |
| Final Adhesion | High N/inch |

Liner

| | |
|-------------------|-----------------------------------|
| Type | Siliconised two side PE Kraft |
| Colour and Finish | White |
| Weight | 144 g/m ² ±10% ISO 536 |
| Thickness | 155 µ ±10% ISO 534 |
| Transparency | n.a. % DIN 53 147-64 |

Applications

For advertising and promotional applications (outdoor and indoor posters, billboards and signs) and for vehicle applications (for flat sided including buses, trams and taxis and for corrugated surfaces and vehicle wrapping).

Printing Methods

The RI-JET series of ink-jet print media gives excellent print results with UV, solvent and eco-solvent ink-jet printing. Testing for suitability between media, printers and inks is always recommended prior to use.

Shelf life

36 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.